

# Cover Strip

Peel & Stick | Use with TPO Membrane



## Overview

Henry Cover Strip is a nominal 60-mil-thick, cured membrane with a nominal 30-mil-thick, fully cured, synthetic rubber peel and stick adhesive.

Cover Strip is ideal for stripping in seams and metal edgings, or simply making repairs to cut Henry TPO Membrane. Cover Strip must be used in conjunction with Henry Low-VOC Primer.

## Features and Benefits

- Compatible with Henry TPO Membrane
- Fully cured state enables it to handle expansion and contraction loads without weakening
- Resists tearing, flex-cracking and abrasion caused by temperature extremes, sunlight, precipitation and all forms of normal weathering

## Size

- 6" x 50' (152 mm x 15.25 m)

## Installation

1. The entire Henry TPO Membrane where Cover Strip will be applied must be clean.

2. Remove all foreign material:

- a. The use of a VOC compliant solvent may be necessary to clean Henry TPO Membrane that has been exposed for a number of weeks.

Permeation-resistant gloves (that meet ANSI/ISEA 105-2005) are required for hand protection when cleaners or primers are being used.

- b. Allow Henry TPO Membrane to dry thoroughly before proceeding.

3. Application of Henry Low VOC Primer:

Roller-apply Henry Low-VOC Primer to Henry TPO Membrane with a short nap-length paint roller. The coated area will be free of globs or puddles.

Note: The use of excessive amounts of Henry Low-VOC Primer will not significantly enhance the adhesion of Cover Strip to Henry TPO Membrane. Use only the amount necessary to obtain 100% coverage of the area where Cover Strip will be applied.

4. Allow Henry Low-VOC Primer to flash off until it does not transfer to a dry finger touch yet remains tacky. Install Cover Strip immediately after Henry Low-VOC Primer has flashed off to promote adhesion and avoid contamination.
5. Peel off 10-12" (250-305 mm) of the protective release liner from Cover Strip. Position Cover Strip over the area to be covered and press down the exposed Cover Strip adhesive using firm, even hand pressure across the entire area. Continue this process until the full area to be flashed is completed maximize bond strength and minimize potential dust contamination.
6. Immediately roll Cover Strip with a 2"-wide (50 mm) roller. Roll across the cover strip edge, not parallel to it.
7. Apply Henry Lap Sealant at overlaps in Cover Strip or at joints in the metal edging.

- To achieve proper adhesion of Cover Strip when jobsite temperatures fall below 40°F (4°C), heat the primed area of Henry TPO Membrane with a hot-air gun as the flashing is applied and pressed into place.

## Precautions

- Prolonged jobsite storage temperatures in excess of 90°F (32°C) will shorten product shelf life.
- In warm, sunny weather, keep Cover Strip rolls in their box and in a shaded area until ready to use.
- Cover Strip must be stored in a dry area.
- Due to solvent flash-off, condensation may form on applied Henry Low-VOC Primer when the ambient temperature is near the dew point. If condensation develops, the application of Henry Low-VOC Primer and Cover Strip must be discontinued as proper adhesion will not be achieved. Allow Henry TPO Membrane to dry before applying a thin coat of Henry Low-VOC Primer and Cover Strip to the previously coated membrane.
- Cover Strip is cured and cannot be used for flashing corners, pipes, or T-joint covers.
- Do not allow waste products (petroleum, grease, oil, solvents, vegetable or mineral oil, animal fats, etc.) or direct steam venting to come in contact with Cover Strip.
- KEEP OUT OF THE REACH OF CHILDREN.

For more information, visit [www.henry.com](http://www.henry.com) or for technical assistance call us at 800-486-1278. Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at [www.henry.com](http://www.henry.com) or by emailing Henry Product Support at [productsupport@henry.com](mailto:productsupport@henry.com) or by calling 800-486-1278.

Henry and #1 Choice of Professionals are registered trademarks of Henry Company.

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.

## Typical Properties and Characteristics

Property	Results
Size	6" x 50' (152 mm x 15.25 m)
Nominal Width – Membrane	6" (152 mm)
Nominal Width – Membrane Adhesive	6-3/8" (155 mm)
Nominal Thickness	90 mil (2.24 mm)
Color	White
Base	Membrane, Adhesive-synthetic rubber
Solids	100%
Tensile Strength	1465 psi typical
Elongation Tear Resistance	540% typical
Ozone Resistance Condition after exposure to 100 pphm Ozone in air for 168 hrs. @ 104°F (40°C) (Specimen under 50% strain)	No cracks
Brittleness Temp	-67°F (-55°C)
Net Weight Per Roll	7.5 lbs (3.5 kg)
Packaging	1 roll/carton
Shelf Life	12 months

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

## LEED® Information

Pre-consumer Recycled Content	0%
Post-consumer Recycled Content	0%
Manufacturing Location	Greenville, IL
Solar Reflectance Index (SRI)	N/A